Ralston Tex Anti-Reflect 1



Mat finish water-based wall and ceiling paint with good hiding power. Biobased and Zero VOC.

- Biobased and Zero VOC
- Excellent coverage
- Perfectly mat
- Non-splashing, smooth application
- No lap marks and a long 'open time' when applying 'full' layer
- High water vapour permeability
- Low odour

www: Ralston Tex Anti-Reflect 1

Application

Situation	Interior
Application	Interior walls and ceilings of plasterboard, plaster, textured plaster, concrete, masonry and mineral-based sheet materials. Can be applied equally well to a new substrate or a substrate previously painted with a latex paint. Ideal for ceilings.

Colors

Colours	White

Performance and features

Binder	Biobased
Pigment	High quality pigments
Density at 20°C	Approx. 1.3 kg/dm3
Viscosity at 20°C	Approx. 128 K.U.
Solids content	Approx. 30 volume %
Drying time (20°C / 65% R.H.)	Dust-free after approx.0.5 hr, recoatable after approx. 4 hr. The stated drying times are typical and depend on such factors as temperature and humidity.
Gloss level	Matt, approx. 1 G.U. at 85°
Scrub resistance	Class 3, as per DIN EN 13 300 after 28 days.
Covering class	Class 2 at economic use of 6 - 9 m2/l as per EN ISO 6504-3 and DIN EN 13 300
Water vapour permeability (SD-value)	sd-value = 0,00 m, class V1: high (SD value < 0.14 m), as per DIN EN 1062-1 and EN ISO 7783-2

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

Processing

Spray data airless - pressure	approx. 20 MPa (200 bar)
Spray data airless - nozzle	0,017 - 0,019 inch

The data in this product data sheet are current at the time of publication. Information on this product is updated regularly and any changes may be made at any time without notice. Ralston Colour & Coatings B.V. disclaims any liability - except in the case of intent or gross negligence - with regard to damage resulting from defects in the accuracy and completeness of the information obtained through this way.

Spray data airless - dilution	none
Spray data air-assisted airless - pressure	10 - 15 MPa (100 - 150 bar), air support approx. 0,2 MPa (approx. 2 bar)
Spray data air-assisted airless - nozzle	0,017 - 0,019 inch
Spray data air-assisted airless - dilution	none
Spray data heated airless 40°C - pressure	15 - 17 MPa (150 - 170 bar)
Spray data heated airless 40°C - nozzle	0,017 - 0,019 inch
Spray data heated airless 40°C - dilution	none
Dilution	Water.
Tools/equipment cleaning	Water.
Application temperature / R.H.	Min. 8 ambient and substrate temp., relative humidity max. 85%.
Theoretical coverage	6 - 9 m2/l
Practical coverage	Per layer 6 - 9 m2/l, depending on the porosity and structure of the substrate. If in doubt, determine on a test area.
Mixing	Stir thoroughly before use.
	The application of a 'full' layer gives a long 'open time' which, combined with 'wet in wet' application, results in a finish that is free of 'lap marks'.

Environment and Health

Flash point (°C)	Not applicable.
Safety instructions	The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.
EU limit value VOC	EU limit value for this product A/a: 30 g/l 2010. This product contains a maximum of 30 g/l VOCs. All whites and base paints are VOC free. Colours made with our Ralston UNI Plus colour pastes are also VOC free.
BREEAM	We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, requirend evidence – completion phase: C 1.1 through to 1.8; in evidence of compliance, the following must be submitted: 1. VOS Volatile Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/a: 30 g/l 2010. This product contains a maximum of 30 g/l VOCs. We apply the above harmonization procedure as recommended by the Dutch Green Building Council.
Belgian emission label	The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.
French emission label	A+

Item details

Packaging	2.5L, 10L
Storage	Cool and above freezing point; do not allow product quality to deteriorate during storage.

The data in this product data sheet are current at the time of publication. Information on this product is updated regularly and any changes may be made at any time without notice. Ralston Colour & Coatings B.V. disclaims any liability - except in the case of intent or gross negligence - with regard to damage resulting from defects in the accuracy and completeness of the information obtained through this way.

Shelf life	Use within 24 months of the date charge no. stated on the pack figures 1 and 2 = year, figures 3 and 4 = month, 5 and 6 = day of the month. Assumes unopened product. After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product.

The data in this product data sheet are current at the time of publication. Information on this product is updated regularly and any changes may be made at any time without notice. Ralston Colour & Coatings B.V. disclaims any liability - except in the case of intent or gross negligence - with regard to damage resulting from defects in the accuracy and completeness of the information obtained through this way.

System structure

New, interior, untreated, masonry

- remove loose parts and any cement skin
- repair where necessary
- pre-treat slightly powdery and/or absorbent substrates with Ralston Wall Primer
- treat entire surface with Ralston Tex Anti-Reflect 1
- treat entire surface with Ralston Tex Anti-Reflect 1

Existing, interior, treated, masonry

- remove unsound paint coats
- repair where necessary
- pre-treat patches with Ralston Wall Primer
- treat patches or entire surface with Ralston Tex Anti-Reflect 1
- treat entire surface with Ralston Tex Anti-Reflect 1

Existing, interior, treated, masonry

- remove unsound paint coats
- repair where necessary
- pre-treat patches with Ralston Tex Anti-Reflect 1
- treat entire surface with Ralston Tex Anti-Reflect 1

The data in this product data sheet are current at the time of publication. Information on this product is updated regularly and any changes may be made at any time without notice. Ralston Colour & Coatings B.V. disclaims any liability - except in the case of intent or gross negligence - with regard to damage resulting from defects in the accuracy and completeness of the information obtained through this way.

General remarks on paint systems and preparation
These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

Adhesion between paint layers
Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

Repairs and compatibility with paint
Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

Pretreatment of masonry
Stony substrates must be solid, load-bearing, sufficiently cured and clean before treatment. Remove any cement/laitance that may be present on cementitious substrates. Cement-bound substrates must be approx. 28 days old before applying a paint or coating. Plaster-bound substrates to be treated may contain max. 2% moisture and other stony substrates max. 4%.

NF DTU 59.1
The substrates must comply with the relevant DTU standards, particularly NF DTU 59.1. Prior assessment is necessary to determine the most suitable preparation based on their condition and nature (cleaning, washing/rinsing, sanding, scraping, degreasing, dulling, dusting...).

Ralston Colour & Coatings B.V.
A brand of Royal Van Wijhe Verf

Russenweg 14
P.O. Box 205
8000 AE Zwolle
Netherlands

T +31(0)38 - 429 11 00
F +31(0)38 - 421 04 14
E info@ralstoncolour.com
W www.ralstoncolour.com

CoC Nr.
05063230

The data in this product data sheet are current at the time of publication. Information on this product is updated regularly and any changes may be made at any time without notice. Ralston Colour & Coatings B.V. disclaims any liability - except in the case of intent or gross negligence - with regard to damage resulting from defects in the accuracy and completeness of the information obtained through this way.